

Sagging Tester (850µm - 1075µm)

BGD 225-5

Product Description

The BGD 225 Sagging Tester, compliant with ASTM D4400 and ASTM D3730, is made of corrosion-resistant stainless steel. It has an application width of 75mm with 6mm per sagging thickness, and gaps are separated by a 1mm space for distinctive identification. These testers are applicable for determining the relative sag resistance of various paints, providing essential technical parameters for on-site paint application.



Standards

- ASTM D 4400
- ASTM D 3730

Technical Specification

Apply the coating on a substrate (glass, test chart, or board) using the appropriate Sagging Tester. Subsequently, position the coated material vertically (90°) on the platform (e.g., a table). Allow 10 to 30 minutes (depending on viscosity) for the coatings to sag under gravity. Examine the coating thickness without the sagging effect and the coating thickness with the sagging effect. Using this information, determine that the recommended coating thickness lies between the two layers of coatings.

Sagging Tester (850µm - 1075µm)

BGD 225-5

Main Technical Parameters

- Material: Stainless Steel
- Difference between adjacent two notches: 25 µm
- Overall dimension: 120 x 20 x 20 mm (L x W x H)
- Weight: 0,5 kg
- Supplied with calibration certificate

Product models	BGD 225-1	BGD 225-2	BGD 225-3	BGD 225-4	BGD 225-5
Clearance Range	50µm - 275 µm	250µm - 475 µm	450µm - 675 µm	650µm - 875 µm	850µm - 1075 µm

- **Ordering Information:** BGD 225-5 - Sagging Tester (850µm - 1075 µm)

Disclaimer

The information given in this sheet is not intended to be exhaustive and any person using the product for any purpose other than that specifically recommended in this sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. Whilst we endeavour to ensure that all advice we give about the product (whether in this sheet or otherwise) is correct we have no control over either the quality or condition of the product or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing to do so, we do not accept any liability whatsoever or howsoever arising for the performance of the product or for any loss or damage (other than death or personal injury resulting from our negligence) arising out of the use of the product. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development