

## **Leveling tester (100-1000µm)**

### **BGD 226-1**

#### **Product Description**

---

BGD 226 Leveling Tester is designed to determine the relative leveling of liquid coating materials before curing in the laboratory. (Coating materials have to eliminate surface defects during drying). It complies with ASTM D2801-1994

It is made of stainless steel with a straight scraper fitted with 5 pairs of notches of increasing depth from 100–1000 µm



#### **Standards**

---

- ASTM D2801-1994

#### **Technical Specification**

---

Once the drawdown has been made on a horizontal, firm surface, leave the coating to cure. After the coating is dry, measure the thickness at which the pairs of film stripes merge

## **Leveling tester (100-1000µm)**

### **BGD 226-1**

#### **Main Technical Parameters**

---

	<b>Wet film thickness</b>	<b>Dimensions (mm) LxWxH</b>
<b>BGD 226-1</b>	100-200-300-500-1000 µm	Gate type 120x20x20
<b>BGD 226-2</b>	10-20-40-80-160 mils*	Gate type 120x20x20

*\* equals 254-508-1016-2032-4064 microns*

Supplied with calibration certificate

Weight: 0.3 KG

#### Ordering Information:

- BGD 226/1 - Leveling Tester (100-1,000µm)
- BGD 226/2 - Leveling Tester (10-160 mils)

#### **Disclaimer**

---

The information given in this sheet is not intended to be exhaustive and any person using the product for any purpose other than that specifically recommended in this sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. Whilst we endeavour to ensure that all advice we give about the product (whether in this sheet or otherwise) is correct we have no control over either the quality or condition of the product or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing to do so, we do not accept any liability whatsoever or howsoever arising for the performance of the product or for any loss or damage (other than death or personal injury resulting from our negligence) arising out of the use of the product. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development