

Tubular Impact Tester: 100 cm / \varnothing 12.7 mm + \varnothing 15.9 mm (ASTM D 2794 / ISO 6272.2)

BGD 305

Product Description

BGD 305 Tubular Impact Tester: 100 cm / \varnothing 12.7 mm + \varnothing 15.9 mm (ASTM D 2794 / ISO 6272.2)

The BGD series Impact Tester produced by our company is in accordance with the specifications in the National Standards for determining paint film resistance to impact and meets the practical requirements of mechanical construction.

The operating principle of the impact tester involves a weight dropping from a specified height, impacting a painted panel under test, leading to rapid deformation. The film's resistance to impact is then determined by observing whether the film cracks or peels off.



Standards

ASTM D 2794

ASTM D 3029

ISO 6272.2

Technical Specification

The impact test describes a method for evaluating the resistance of a dry film of paint, varnish, or a related product to cracking or peeling from a substrate when subjected to deformation caused by a falling weight. The coating under test is applied to suitable, thin, normally metal panels. After the coating has cured, a standard weight is dropped on each panel from a height that will cause deformation of the coating and the substrate. The test can be carried out with the coated side of the panel facing upwards, i.e., towards the falling weight, or downwards, i.e., away from the weight. By gradually increasing the height from which the weight drops, the point at which failure occurs can be determined. Films generally fail by cracking, which is made more visible by the use of a magnifier.

The test can be carried out:

1. a) either as a 'pass-fail' test, meaning the test is carried out from one drop height and with a specified mass, to test compliance with a particular specification.

Tubular Impact Tester: 100 cm / ø12.7 mm + ø15.9 mm (ASTM D 2794 / ISO 6272.2)

BGD 305

2. b) or as a classification test, to determine, by gradually increasing the drop height and/or the mass, the minimum mass and/or drop height for which the coating cracks or peels from its substrate.

We offer many different types of impact testers according to different standards. These impact testers consist of a solid base with a guide tube support, various weights of falling hammers, and different diameter punches. Users can choose a different size and weight hammer to simulate paint used in different environments.

Tubular Impact Tester: 100 cm / \varnothing 12.7 mm + \varnothing 15.9 mm (ASTM D 2794 / ISO 6272.2)

BGD 305

Main Technical Parameters

Ordering information	BGD 302	BGD 304	BGD 305	BGD 306
Technical Parameter				
Instrument scale length	0-50cm	0-100cm	0-100cm(40inch)	0-100cm(40inch)
Graduation	1cm	1cm	1cm	1cm
Mass of hammer	1Kg	1Kg	1000g(2 pcs) 300g(1 pc)	1000g(2 pcs) 2 lb.(2 pcs)
Piercer specification	\varnothing 8mm	\varnothing 8mm	\varnothing 12.7mm(1/2 inch) \varnothing 15.9mm(5/8 inch)	\varnothing 20 mm \varnothing 15.9mm(5/8 inch)
Notch diameter on the bolster block	\varnothing 15mm	\varnothing 15mm	\varnothing 16.3mm \varnothing 31.75mm	\varnothing 27mm \varnothing 16.3mm(41/64inch)
Impact depth of piercer	2mm	2mm	2.5mm	2.5mm
Standard	GB/T 1732	GB/T 1732	ASDM D 2794 ISO 6272.2	ISO 6272.1

Disclaimer

The information given in this sheet is not intended to be exhaustive and any person using the product for any purpose other than that specifically recommended in this sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. Whilst we endeavour to ensure that all advice we give about the product (whether in this sheet or otherwise) is correct we have no control over either the quality or condition of the product or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing to do so, we do not accept any liability whatsoever or howsoever arising for the performance of the product or for any loss or damage (other than death or personal injury resulting from our negligence) arising out of the use of the product. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development