

Perm Cups

Perme Cup - Anodized Aluminium - 10 cm2

Product Description

Perm cups are used to determine the permeability of films to the vapor of water and other liquids. Materials that are tested include paint, varnish, thin plastic films and other types of sheets thin enough to be tightly sealed in place across the face of the cup. Permeability is expressed as the weight of a vaporous material that passes through a specified area and thickness of free film within a specified time interval under controlled conditions. These Perm Cups are made up of three basic parts, each machined from the highest grade anodized aluminum. The cup top surface, as well as both surfaces of the clamp ring are smoothly finished to provide a tight seal against the product under test. Two gaskets with the same dimensions as the clamp ring, except for thickness, are furnished for use with rough or uneven materials to insure complete sealing. Extending upward from the face of the cup are two stainless steel pins which closely engage the clamp ring, and any gaskets used, to prevent movement with respect to the test material as the cap is tightened against the cup. The cap design permits use of longer pins than possible with earlier models to accommodate thicker sample and gasket combinations.

Perm Cup is designed to be in complete compliance with ASTM Method D 1653



Standards

ASTM D 1653

Technical Specification

Material: Anodized Aluminium

Volume: 10 cm2



Perm Cups

Perme Cup - Anodized Aluminium - 10 cm2

Main Technical Parameters

Ordering information: BGD 340-1 Perm Cup 10cm2

Disclaimer

The information given in this sheet is not intended to be exhaustive and any person using the product for any purpose other than that specifically recommended in this sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. Whilst we endeavour to ensure that all advice we give about the product (whether in this sheet or otherwise) is correct we have no control over either the quality or condition of the product or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing to do so, we do not accept any liability whatsoever or howsoever arising for the performance of the product or for any loss or damage (other than death or personal injury resulting from our negligence) arising out of the use of the product. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development